



INVESTOR IN PEOPLE

The Patent Office
Concept House
Cardiff Road
Newport
South Wales
NP10 8QQ

GB *EP04/8656*

I, the undersigned, being an officer duly authorised in accordance with Section 74(1) and (4) of the Deregulation & Contracting Out Act 1994, to sign and issue certificates on behalf of the Comptroller-General, hereby certify that annexed hereto is a true copy of the documents as originally filed in connection with the patent application identified therein.

In accordance with the Patents (Companies Re-registration) Rules 1982, if a company named in this certificate and any accompanying documents has re-registered under the Companies Act 1980 with the same name as that with which it was registered immediately before re-registration save for the substitution as, or inclusion as, the last part of the name of the words "public limited company" or their equivalents in Welsh, references to the name of the company in this certificate and any accompanying documents shall be treated as references to the name with which it is so re-registered.

In accordance with the rules, the words "public limited company" may be replaced by p.l.c., plc, P.L.C. or L.C.

Re-registration under the Companies Act does not constitute a new legal entity but merely subjects the company to certain additional company law rules.

Signed

Andrew Gersey

Dated 29 July 2004

**PRIORITY
DOCUMENT**

SUBMITTED OR TRANSMITTED IN
COMPLIANCE WITH RULE 17.1(a) OR (b)

Patents Form 1/77

Patents Act 1977
(Rule 16)THE PATENT OFFICE
DL
22 AUG 200322AUG03 E83282-1/C59642
P01/7700 0.00-0319781.1

Request for grant of a patent

(See the notes on the back of this form. You can also get an explanatory leaflet from the Patent Office to help you fill in this form)

The Patent Office

Cardiff Road
Newport
South Wales
NP10 8QQ

1. Your reference	PAT 51110/GB		
2. Patent application number (The Patent Office will fill in this part)	0319781.1		22 AUG 2003
3. Full name, address and postcode of the or of each applicant (underline all surnames)	Imperial Chemical Industries Plc 20 Manchester Square London W1U 3AN		
Patents ADP number (if you know it)	935006		
If the applicant is a corporate body, give the country/state of its incorporation	United Kingdom		
4. Title of the invention	COATING COMPOSITIONS		
5. Name of your agent (if you have one)	ANDREW FRANGOU		
"Address for service" in the United Kingdom to which all correspondence should be sent (including the postcode)	ICI Paints ICI Group Intellectual Property P O Box 1883 Wexham Road Slough PDO Berkshire SL2 5FD		
Patents ADP number (if you know it)	6366090003		
6. If you are declaring priority from one or more earlier patent applications, give the country and the date of filing of the or of each of these earlier applications and (if you know it) the or each application number	Country	Priority application number (if you know it)	Date of filing (day / month / year)
	N/A		
7. If this application is divided or otherwise derived from an earlier UK application, give the number and the filing date of the earlier application	Number of earlier application	Date of filing (day / month / year)	
	N/A		
8. Is a statement of inventorship and of right to grant of a patent required in support of this request? (Answer 'Yes' if: a) any applicant named in part 3 is not an inventor, or b) there is an inventor who is not named as an applicant, or c) any named applicant is a corporate body. See note (d))	YES		

Patents Form 1/77

Patents Form 1/77

9. Enter the number of sheets for any of the following items you are filing with this form. Do not count copies of the same document

Continuation sheets of this form

Description

18 ✓

Claim(s)

2 ✓

Abstract

1 ✓

Drawing(s)

10. If you are also filing any of the following, state how many against each item.

Priority documents

N

Translations of priority documents

N

Statement of inventorship and right to grant of a patent (Patents Form 7/77)

1 ✓

Request for preliminary examination and search (Patents Form 9/77)

N

Request for substantive examination (Patents Form 10/77)

N

Any other documents (please specify)

Request for permission to file abroad sent separately

S177 + Declaration

11.

I/We request the grant of a patent on the basis of this application.

Signature

ANDREW FRANGOU

Date

22/8/03

(Agent for Applicant)

12. Name and daytime telephone number of person to contact in the United Kingdom

ANDREW FRANGOU

01753 877123

Warning

After an application for a patent has been filed, the Comptroller of the Patent Office will consider whether publication or communication of the invention should be prohibited or restricted under Section 22 of the Patents Act 1977. You will be informed if it is necessary to prohibit or restrict your invention in this way. Furthermore, if you live in the United Kingdom, Section 23 of the Patents Act 1977 stops you from applying for a patent abroad without first getting written permission from the Patent Office unless an application has been filed at least 6 weeks beforehand in the United Kingdom for a patent for the same invention and either no direction prohibiting publication or communication has been given, or any such direction has been revoked.

Notes

- If you need help to fill in this form or you have any questions, please contact the Patent Office on 08459 500505.
- Write your answers in capital letters using black ink or you may type them.
- If there is not enough space for all the relevant details on any part of this form, please continue on a separate sheet of paper and write "see continuation sheet" in the relevant part(s). Any continuation sheet should be attached to this form.
- If you have answered 'Yes' Patents Form 7/77 will need to be filed.
- Once you have filled in the form you must remember to sign and date it.
- For details of the fee and ways to pay please contact the Patent Office.

Patents Form 1/77

DE PINNA
SCRIVENER NOTARIES

I, **ANDREW NICHOLAS ROBINSON**, Notary Public of the City of London and elsewhere in England, by Royal Authority duly admitted and sworn, practising in the said City,

DO HEREBY CERTIFY AND ATTEST:

THAT the Seal affixed at foot of the hereunto annexed Power of Attorney is the genuine Common Seal of "**IMPERIAL CHEMICAL INDUSTRIES PLC**", a Company duly incorporated and existing in accordance with the laws of England, registered at the Companies Registration Office for England and Wales under N°. 218019 and having its Registered Office at Imperial Chemical House, Millbank, London SW1P 3JF, England;

THAT the signatures set and subscribed at foot of the said Power of Attorney are truly those of **TIMOTHY ALEXANDER SCOTT** and **DEBJANI JASH**, whose identities I attest, one of the Directors and the Secretary, respectively, of the said Company;

AND THAT the said Power of Attorney, being so sealed and signed, is binding on the said Company in accordance with the provisions of English law.

IN TESTIMONY WHEREOF I have hereunto set my hand and affixed my Seal of Office in the City of London aforesaid, this ninth day of November in the year Two thousand and one.



A. N. ROBINSON
Scrivener Notary of London, England



DE PINNA

35 Piccadilly London W1J 0LJ

Telephone: 44 (0)20 7535 7852 Fax: 44 (0)20 7535 7853 E-mail: a.n.r@depinna.co.uk

0077967/22-Aug-03:02:58

GENERAL POWER FOR PATENTS REGISTERED DESIGNS AND UTILITY MODELS

BY THIS DEED IMPERIAL CHEMICAL INDUSTRIES PLC a company incorporated in England and Wales having its registered office at 9 Millbank, London SW1P 3JF ("the Company") **ANDREW FRANGO** to be its true and lawful Attorney ("the Attorney") for and on behalf of the Company to act either alone or jointly or severally with any other person or persons similarly authorised by the Company to:-

1. sign and execute applications for Patents, Registered Designs and Utility Models in all countries of the world;
2. sign any documents relating to and execute applications for the recording of any assignment or licence of Patents, Registered Designs or Utility Models in all countries of the world;
3. sign and execute all other documents pursuant to all proceedings established under the laws and regulations relating to Patents, Registered Designs or Utility Models in all countries of the world;
4. pay the lawful fees and taxes and to receive payments on its behalf which the said Attorney may deem to requisite;
5. appoint any agent or agents and delegate to him or them all or any of the powers and authorities hereinbefore conferred as the Attorney may think fit and to revoke and cancel all or any of such powers and authorities; and
6. **GENERALLY** to do sign execute give and accept all such deeds documents acts notices requisitions communications and things as may be necessary for all or any of the purposes aforesaid.

Nothing in this Deed shall grant or be deemed to grant any power to the Attorneys to assign or license any of the Company's rights in any Patents, Registered Designs or Utility Models.

The Company shall ratify and confirm whatsoever the Attorney shall lawfully do in the proper exercise of the power hereby granted.

This Power of Attorney revokes all previous Powers of Attorney in relation to its subject matter including but not limited to that dated 6th September 1994 and

shall unless previously revoked cease and determine absolutely on the third anniversary of the date hereof.

In WITNESS WHEREOF the Company has caused its common seal to be affixed hereunto this ^{6th} day of ~~September~~ ²⁰⁰¹ Two Thousand and One.

EXECUTED AND DELIVERED)
AS A DEED of IMPERIAL)
CHEMICAL INDUSTRIES PLC)
in the presence of:

Director:

TAScott

Company Secretary:

Sy - 6

I947V2

Coating Composition

10 The present invention relates to fire retardant coating compositions, their preparation and use.

15 Coating compositions are commonly used to coat the surfaces found in buildings, for example walls, ceilings, floors and furniture. Such surfaces are usually coated at ambient temperature of about 5 to 40°C using brushes, rollers, pads or sprays. The coatings include paints, lacquers and varnishes. Such coatings can burn in the event of a fire in a building.

20 Fires inside buildings and other structures cause substantial damage and often loss of life both from the heat of the blaze as well as the smoke generated. A source of fuel in such fires is the coating on the surfaces found inside buildings. Of course, such surfaces are often repainted many times and, over the years, it is not uncommon to have ten or more coats of dried paint thereon.

25 Such multiple coats of paint, although unlikely to be the initial source of the

fire, will certainly feed it thereby prolonging its duration and increasing the damage caused. To be effective in real life situations, therefore, fire retardant coatings must be of low flammability themselves as well as sufficiently robust to maintain their integrity in a fire such that the paint layers and other substrates beneath are substantially prevented from igniting.

In order to make objective comparisons, a system of certification by national bodies has been set up. Such certifying bodies have developed various testing protocols to assess the effectiveness of the fire retardant coatings. These vary in severity by specifying different substrates, for example flammable versus non-flammable and whether or not the substrate is overcoated with previous dried layers of flammable paint. An example of the most severe test is BS 476 titled Fire Tests on Building Materials and Structures which is hereby incorporated by reference; part 6 of this relates to methods of tests of fire propagation of products and part 7 to surface spread of flames for materials. The most challenging substrate for the test is the Warrington blue board which is plasterboard coated with 10 layers of different paints. This is then coated with a fire retardant coating, subjected to the test and the result assessed

Known fire retardant coating compositions contain fire retardant materials. In addition, such coatings may also contain polymeric binder, particulate non-binder solids such as inorganic and/or organic pigments (for example rutile titanium dioxide) and/or extenders (for example clays or talc) as well as other optional ingredients such as structuring agents (for example laponite or bentonite clays), coalescing solvents (for example benzyl alcohol or white spirit), antifoaming agents and biocides.

The volume of particulate matter contained in a dry coating compared with the total volume of the dried coating (including polymeric binder) is known as the pigment volume concentration or PVC. In this context the term pigment includes all matter which in the final film remains particulate. The concept of PVC also applies to polymeric moulding formulations.

Typical of the fire retardant materials referred to above include organic halogen compounds such as chlorinated paraffins and brominated materials. Chlorinated polymers and copolymers such as polyvinyl chloride and polyvinylidene chloride are themselves fire retardant by virtue of their high chlorine content. The halogenated materials may be used alone or together with antimony compounds such as antimony trioxide or antimony pentoxide which are thought to act as synergists. One proposed mechanism for the mode of action of the halogenated and mixed antimony-halogenated systems is that they interfere with the mechanism responsible for producing high energy radicals in the gas phase of the flame thereby reducing the magnitude of the flame and/or its temperature. Such agents are effective but they tend to produce high smoke density and corrosive gases in the fire causing more damage. Furthermore, handling antimony compounds and halogenated materials during the paint-making process is itself a cause of concern for the health and safety of the workers involved. Dust produced by sanding flame retardant paint containing antimony creates an additional hazard for the environment.

Alternatives to the halogen fire retardants include a class of compounds that produce water vapour or carbon dioxide at elevated temperature. Examples of such materials are the metal carbonates such as Huntite ($3\text{MgCO}_3 \cdot \text{CaCO}_3$) and Hydromagnesite ($\text{Mg}_5(\text{CO}_3)_4(\text{OH})_2 \cdot 4\text{H}_2\text{O}$) and metal hydroxides, such as

aluminium trihydroxide also known as aluminium trihydrate; and magnesium hydroxide. These are also sometimes referred to as fire retardant fillers. In the early stages of the fire such filler materials are believed to release the carbon dioxide or water thereby preventing flames taking hold or extinguishing any flames that have already taken hold. However, a known disadvantage is that they are not very effective at high temperature.

At higher temperatures, materials capable of producing glass-like chars can be more effective. Zinc borate is an example of such a material. The chars thus formed are thought to act as a physical barrier blocking heat reaching the substrate beneath the painted surface. Unfortunately, such glassy chars are very brittle and have a tendency to fall off the very article they are intended to protect. More recently mixtures of glass-like materials and ceramic-like materials have become available and these produce glassy chars that are more robust.

In addition to these are the coatings producing fire retardancy by intumescence, by which is meant an insulating foam is produced at the temperatures found in a fire. Typically, an acid source, a charring source and a foaming agent are required. The acid source is a phosphorus compound generating phosphoric acid at high temperature. The charring source may be any source of carbon; the polymer of the film forming resin can be sufficient. The blowing agent is typically urea producing ammonia at high temperature. However, intumescent coatings often have poor decorative properties and overcoating them with conventional, that is non-fire retardant, coatings generally creates problems of wetting which can result in an unattractive final appearance.

EP 0 833 862 discloses a process for coating inorganic filler particles such as magnesium hydroxide or aluminium trihydroxide with certain tin compounds. The use of such coated filler particles as fire retardants in low PVC (that is less than 15%) polymer moulding formulations is also disclosed. These moulding formulations, however also contain halogenated materials such as polyvinyl chloride as the polymeric binder or Cerechlor 70, a chlorinated paraffin wax, which are themselves known to be effective as fire retardants due to their high chlorine content as discussed above. Of course the presence of the chlorine produces dense smoke and corrosive gases during combustion.

EP 0 833 862 also mentions coating compositions although specific formulations are not revealed and high PVC, halogen free coatings are not disclosed.

Surprisingly, we have now found that halogen-free coating compositions can be made at very high PVC and of improved fire retardant properties.

Accordingly, there is provided a halogen-free fire retardant coating composition comprising film forming polymer and inorganic fire retardant material characterised in that the fire retardant material comprises a combination of fire retardant filler particles and a metal stannate and/or a metal hydroxy stannate wherein the overall PVC of the composition is from 75 to 97 %.

Preferably the fire retardant material of the coating composition is able to give

off water and/or carbon dioxide when the dried coating is exposed to the elevated temperatures found in or close to a flame in a fire. More preferably the fire retardant filler is selected from the group consisting of huntite, hydromagnesite, aluminium trihydroxide and magnesium hydroxide.

The metal stannates may be represented by $M\text{SnO}_3$ and the metal hydroxy stannates by $M\text{Sn}(\text{OH})_6$. Preferably the metal represented by M is zinc, magnesium, calcium, strontium, barium, iron, cobalt, nickel or copper. Preferably the metal is zinc as this produces effective fire retardancy as well as being substantially colourless. Even more preferably the metal hydroxy stannate is zinc hydroxy stannate.

Preferably the fire retardant material comprises the fire retardant filler particles coated with the metal stannate and/or the metal hydroxy stannate as this produces more effective fire retardancy. More preferably, the coating is bound to the filler particles. A suitable example of a fire retardant filler coated with a metal hydroxy stannate is aluminium trihydrate coated with zinc hydroxy stannate, available as Storflam ZAHTM.

Preferably the fire retardant material comprises from 100 to 2000% and more preferably from 300 to 1500% by weight of the film forming polymer. Most preferably, the fire retardant material comprises from 900 to 1400% as this produces the optimum balance of fire retardancy and other dried coating properties.

Preferably the PVC is from 80 to 97%; more preferably from 85 to 95% and

7

even more preferably from 87 to 93%. Preferably at least 65% of the PVC of the composition is provided by the fire retardant material.

Although not wishing to be bound by this theory, the very high PVC of the coatings of the invention not only allows very high levels of fire retardant materials to be incorporated into the dried coating, it also results in a minimum amount of film forming polymer in the coating. As it is the film forming polymer that is the main flammable material, fire retardancy is thereby further improved.

Formulating at such high PVC can reduce some of the desirable properties of the coating composition. In particular, there is a tendency for the wet coating to form fissures as it dries creating a dried, solid coating with cracks in it. This not only produces an undesirable appearance but, of course, reduces the fire retardant properties of the coating resulting from the exposure of the flammable material beneath to flames and heat.

Large particle size materials may be used to overcome this problem. By large in this context is meant that the particle size distribution extends from sub-micron up to 1000 microns, preferably from 0.1 to 750 microns, more preferably from 0.1 to 500 microns and still more preferably from 0.1 to 200 microns. Most preferred are particle size distributions where from 50 to 90 % by weight of the particles are up to 50 microns and from 5 to 25% by weight are from greater than 50 to 100 microns and from 5 to 25% by weight are from greater than 100 to 200 microns. Particles above about 200 microns can produce a textured look in the dried coating so where a smooth final appearance is required the particle size distribution is preferably substantially

free of particles greater than 250 microns. Where the particles are substantially spherical the size refers to the diameter. Where the particles are non-spherical the size refers to the largest dimension. However, materials having a high aspect ratio, such as fibres, tend to bend and coil in the dried coating. Coatings can thus be formulated with fibres of up to about 3 mm in length and not exhibit significant texture in the dried coating. These may be selected by routine experiment.

Although the size and distribution of the particles largely determines their effectiveness in preventing the cracks and other defects from forming, the type of the material itself will affect the fire retardancy of the coating composition. Preferably non-flammable materials are used. More preferably, inorganic materials are used.

Suitable examples of such non-flammable materials include fly ash, calcium carbonate, clays, talc and glass fibres or spheres. Fly ash comprises hollow alumina-silicate spheres extracted from pulverised fuel ash. Fillite™ 200/7 is a suitable example of the fly ash type. Examples of suitable glass fibres are available from Wrigley Fibres, F.H.Wrigley Ltd in Somerset, England TA4 4RF under the tradename PAN™ fibres or from Fibertec Inc, Bridgewater, Michigan, USA 023204, under the tradename Microglass™. Suitable examples of hollow glass spheres are available from Wrigley Fibres as glass micro balloons.

Preferably, such materials comprise from 5 to 40 % by weight of the coating formulation, more preferably from 10 to 30 % by weight of the coating formulation and even more preferably from 15 to 25% by weight of the

coating formulation.

Preferably the coating composition is waterborne as this reduces the amount of organic solvent released to the atmosphere during drying of the applied coating. Such solvents in the atmosphere are considered hazardous to the environment and in many cases the users of the paint dislike the odour they produce. By waterborne is meant that at least 50% by weight of the volatile material or the carrier liquid of the coating composition is water. More preferably the organic solvent level is from 0.1 to 30% and even ore preferably from 0.5 to 10% by weight of the total paint composition. Most preferably he coating composition is substantially free of organic solvent. Preferably, where organic solvents are used, for example to improve substrate wetting or dispersion of the particulate matter, water compatible or water-soluble solvents are used. Examples of such suitable solvents include propylene glycol, benzyl alcohol, texanol and white spirit.

Organic solvents, preferably water compatible organic solvents are also useful in increasing the open time of the coating; that is they extend the time it takes for the coating composition to dry. This is especially important for coatings formulated at PVC above about 75% as they have a tendency to form defects during drying.

It is preferred that the coating composition is 1 pack. By this is meant that the liquid coating composition may be used direct from the container. Furthermore, other than perhaps reducing the viscosity by the addition of solvent, say water, no further essential ingredients are required to be mixed in order for the coating to develop its intended properties as a fire retardant

coating. Such a ready for use coating composition has the additional advantage that it does not have a limited 'pot life' beyond which any unused coating must be discarded.

5 Suitable film forming resins include addition polymers and condensation polymers. The term polymer is used herein to describe both homopolymers and copolymers.

10 Suitable examples of addition polymers can be derived from acrylic acid esters and methacrylic acid esters, amides, nitriles, vinyl monomers such as styrene and its derivatives and vinyl esters such as vinyl acetate and vinyl versatate.

15 Using the nomenclature (meth)acrylate to represent both acrylate and methacrylate, suitable (meth)acrylic acid esters include the alkyl esters, preferably methyl (meth)acrylate, propyl (meth)acrylate, butyl (meth)acrylate, 2-ethyl hexyl (meth)acrylate and alkoxy poly(oxyethylene) (meth)acrylate. Small amounts of acrylic acid and/or methacrylic acid may also be used. Hydroxy functional monomers such as hydroxy ethyl (meth)acrylate and/or hydroxy isopropyl (meth)acrylate, may also be included. Preferably the
20 addition polymer is derived from the esters of (meth)acrylic acid. More preferably the addition polymer is derived from methyl methacrylate, 2-ethyl hexyl acrylate and acrylic acid and even more preferred is where the weight ratio of these monomers is 50.5:48.5:1.0. respectively.

25 Suitable examples of condensation polymers include polyesters and polyurethanes. Urethane-acrylic hybrid polymers, where the urethane and

acrylic addition polymer portion are closely associated may also be used.

The glass transition temperature, or Tg of the addition polymer may be varied by copolymerising monomers of appropriate Tg. Similarly, by varying the amount of hard and soft coreactants the Tg of the condensation polymers may also be varied. In this way polymers which are hard, soft or intermediate Tg can be made which can produce a range of desirable physical properties, such as hardness in the dried coating.

10 Preferably Tg of the polymer used as the film forming resin is from -60°C to 130°C, more preferably from -50°C to 70°C and even more preferably from -30 to 30°C. The lower Tg polymers are preferred as they allow a coherent dried coating to form even at very high PVC.

15 The film forming resin may be a solution polymer by which is meant that the polymer is dissolved in organic solvent or water; or a dispersion polymer where the polymer exists as particles dispersed in a liquid carrier medium. Such dispersions are often referred to as latexes. Preferably the film forming resin is a dispersion polymer and more preferably the liquid carrier medium is
20 substantially water. The weight average particle diameter of such latexes is preferably from 0.01 to 5 microns, more preferably from 0.1 to 3 microns and most preferably for 0.1 to 1 microns.

Preferably they are made by emulsion polymerisation process.

25

The wet coating should be applied to the substrate at a thickness sufficient to

12

produce a dried coating thickness of from 0.3 to 3.0 mm, preferably from 0.5 to 2.0 mm and most preferably from 0.8 to 1.25 mm. At higher dried coating thickness, for example greater than 0.5 mm, more than one coat may be required. Preferably, dried coating thickness of 2 mm can be achieved in 1 or 2 coats. This can be achieved by brush or roller application although roller application is preferred.

In order to achieve such coating thicknesses the medium shear viscosity should be, preferably from 1.5 to 6.0 Pa.s, preferably from 2.0 to 5.0 Pa.s and more preferably from 2.0 to 4.0 Pa.s. The viscosity is measured at 25°C using a Rotoviscometer (available from Sheen Instruments, Teddington, London, England) fitted with a 1.25 inch (3.175 cm) spherical bob (part number 455N/65) rotating at 562 rpm.

Other important paint properties are also affected by the very high PVC of the invention. For example, stain resistance and scrub resistance may be unacceptably poor. In these circumstances the dried layer of fire retardant coating composition may be overcoated with a second different layer of conventional coating which, although is itself not fire retardant to the extent of the coating compositions provided by this invention, nevertheless does have acceptable stain and scrub properties. Surprisingly, such a system has good fire retardant properties.

Accordingly, there is provided a fire retardant coating system, comprising a first dried layer of fire retardant coating composition and a second dried layer of coating composition characterised in that the second layer is of a different composition. Preferably the second layer is coloured.

Such a two product system has the added advantage that a fire retardant system can be produced offering a range of colours without the need to formulate a range of coloured compositions which are themselves fire retardant. Optionally, the second coating layer is fire retardant.

In cases where the adhesion between the fire retardant coating composition and the substrate is poor or inadequate, it is preferred that the coating system comprises a layer of primer, between the substrate and the fire retardant coating in order to increase the adhesion to acceptable levels. Such primers are often referred to as adhesion promoting primers. The primer may itself be fire retardant.

The invention also provides a coated wall, ceiling, floor or articles characterised in that said wall, ceiling, floor or article is coated with a coating of the invention.

The invention is further illustrated by the following examples.

The ingredients referred to in the examples are listed below and are available from the suppliers listed.

Bentone™ EW, a clay thickener is available from Elementis, Stolbergerstrasse 370, Cologne, Germany.

Dispelair™ CF246, an antifoam is available from Blackburn Chemicals Ltd at

Whitebirk Industrial Estate, Blackburn, England, BB1 5SX

Acticide™ CHR 010, a biocide is available from Thor at Wincham Avenue, Wincham, Northwich, Cheshire, England, CW9 6GB

Orotan™ 731 and Acrysol SCT-275, a dispersant and thickener respectively are available from Rohm & Haas at Lennig House, 2, Masons's Avenue, Croydon, Surrey, England, CR9 3NB

Propylene Glycol is available from Petrochem Carless at Cedar Court, Guildford Road, Leatherhead, Surrey, England, KT22 9RX

Disponil™ A1580, a dispersant is available from Cognis at 40551 Dusseldorf, Germany

Storflam™ ZAH is available from Joseph Storey & Co Ltd at Heron Chemical Works, Moor Lane, Lancaster, England, LA1 1QQ

Natrosol™ 250 MR and Aquaflo™ NHS 300, both thickeners, are available from Hercules BV Aqualon Division, at Noordweg 9, PO Box 71, 3330 AB Zwijndrecht, The Netherlands

Fillite™ 200/7 is available from Fillite at Goddard Road, Astmoor Industrial Estate, Runcorn, Cheshire, England

Microglass™ 3004, glass fibres is available from Fibertec Inc at 35, Scotland Boulevard, Bridgewater, MA 02324, USA

Warrington Blue Boards are available from Warrington Fire Research Centre, Holmesfield Road, Warrington, Wa1 2DS, England

DULUX™ Trade Vinyl Matt White is available from Imperial Chemical Industries, Wexham Road, Slough, Berkshire, SL2 5DS, England

Examples

Example 1

To a 2.5 litre container (diameter 150mm) fitted with a dispersion impeller blade of 100mm diameter is added the first portion 564.6g of Tap Water (1) and 23.2 g of BentoneTM EW whilst stirring at 500 to 1000 rpm. Stirring is continued for about 5 minutes until a uniform dispersion is formed with no obvious signs of agglomeration. To this mixture is added, whilst stirring and in the order indicated in Table 1, the ingredients of Portion B in the amounts shown. StorflamTM ZAH is added slowly over a period of about 3 minutes. When all of the ingredients are added to the container, the resulting mixture of Portion A and Portion B are dispersed using high speed stirring at 2000 to 3000 rpm for about fifteen minutes to form the millbase. The ingredients of Portion C are then added in the order indicated in Table 1 with slow speed stirring of about 350 rpm using a Heidolph stirrer fitted with a 100 mm diameter paddle blade until a uniform consistency is achieved to form the final coating composition.

TABLE 1

	Wt%	g
<u>MILLBASE</u>		
<u>Portion A</u>		
Tap water (1)	18.435	564.6
Bentone EW	0.759	23.2
<u>Portion B</u>		
Dispclair CF246	0.205	6.3

16

Acticide CHR 010	0.198	5.8
Orotan 731 (25%)	1.230	37.7
Propylene Glycol	2.374	72.7
Disponil A1580	0.205	6.3
Storflam ZAH	42.73	1308.7
Natrasol 250MR	0.040	1.2
Tap Water (2)	2.612	80.0

Portion C

Fillite 200/7	21.093	646.0
Acrylic polymer latex*	5.822	178.3
Acrysol SCT-275	0.957	29.3
Microglass 3004	2.391	73.2
Aquaflow NHS 300	0.096	29.3

*The acrylic polymer latex is made by an emulsion polymerisation process and has a monomer composition of methyl methacrylate/2-ethyl hexyl acrylate/acrylic acid of weight ratio 50.5/48.5/1.0 respectively with a calculated Tg of 6.4°C. The solids content is 50% by weight.

The non volatile content of the coating is 53% by weight.

The Rotathinner viscosity measured at 25 °C was 3 Pa.s.

Comparative Example A

Dulux Trade White Vinyl Matt paint was used as a standard.

The Rotothinner viscosity measured at 25 °C was 0.83 Pa.s.

Test Method

A Warrington Blue Board supplied by the manufacturer pre-coated with 10 layers of paint. The specimen board is prepared by applying the test coating to the Warrington Blue board and allowing it to dry and age for 3 days.

10 This specimen board is tested according to BS 476 part 7, a summary of which is detailed below.

The specimen is mounted in a water-cooled holder and is exposed to a radiant panel for 10 minutes. In addition a pilot flame is applied to the bottom corner
15 of the specimen during the first minute of the test. The time required for the flame front to reach reference marks on the specimen is noted, together with the extent of the flame spread at 1.5 minutes and 10 minutes after the beginning of the test.

20 Testing

Specimen 1

The fire retardant coating composition of Example 1 was applied to the prepared aged board in two coats using a medium length pile (about 12 mm) roller and allowed to dry. A dried coating thickness of 1100 microns (1.1
25 mm) was achieved. This was allowed to age for 3 days before being submitted

to the BS 476 part 7 test to assess fire retardancy. After 1.5 minutes the flame had spread 40 mm and after 10 minutes had spread 50 mm from the reference point.

Specimen 2

Warrington Blue board was prepared according to Specimen 1 and then further coated with the coating composition of Comparative Example A. The dried coating thickness achieved was 1100 microns and 150 microns respectively. This was allowed to dry and age for 3 days before testing according to BS 476 part 7 to assess fire retardancy. After 1.5 minutes the flame had spread 40 mm and after 10 minutes had spread 50 mm from the reference point.

Specimen A

Dulux Trade Vinyl Matt of Comparative Example A was applied to the prepared aged board using the same method as in Example 1. A dried coating thickness of 150 microns was achieved. This was allowed to dry and age for 3 days before testing according to BS 476 part 7 to assess fire retardancy. After 1.5 minutes the flame had spread 300 mm and after 10 minutes had spread 440 mm from the reference point.

The spread of the flame when using the coating compositions of the invention is shown to be significantly reduced.

Claims

1) A halogen-free fire retardant coating composition comprising

- i) film forming polymer
- ii) inorganic fire retardant material

characterised in that the fire retardant material comprises a combination of fire retardant filler particles and a metal stannate and/or a metal hydroxy stannate wherein the overall PVC of the composition is from 75 to 97 %

2) A fire retardant coating composition according to Claim 1 characterised in that the fire retardant material comprises fire retardant filler particles coated with the metal stannate and/or the metal hydroxy stannate.

3) A fire retardant coating composition according to Claim 1 or Claim 2 characterised in that the inorganic fire retardant material is able to give off water and/or carbon dioxide when in the form of a dried coating and exposed to the elevated temperatures found in or close to a flame in a fire.

4) A fire retardant coating composition according to any one of the preceding Claims characterised in that the fire retardant filler is selected from the group consisting of huntite, hydromagnesite, aluminium trihydroxide and magnesium hydroxide.

5) A fire retardant coating composition according to any one of the preceding Claims characterised in that the metal hydroxy stannate is zinc hydroxy stannate.

6) A fire retardant coating composition according to any one of the preceding Claims characterised in that the fire retardant material comprises from 100 to 2000% by weight of the film forming polymer.

7) A fire retardant coating system comprising a first dried layer of fire retardant coating composition according to any one of the preceding claims

20

and a second dried layer of coating composition characterised in that the second layer is of a different composition to the first.

8) A coated wall, ceiling, floor or article characterised in that said wall, ceiling, floor or article is coated with a coating according to anyone of the preceding claims.

9) A coating composition substantially as hereinbefore described by reference to Example 1 or Example 2.

21

Abstract

A halogen-free fire retardant coating composition comprising film forming polymer, inorganic fire retardant material characterised in that the fire retardant material comprises a combination of fire retardant filler particles and a metal stannate and/or a metal hydroxy stannate wherein the overall PVC of the composition is from 75 to 97 % .

10

15

20

PCT/EP2004/008656



**This Page is Inserted by IFW Indexing and Scanning
Operations and is not part of the Official Record**

BEST AVAILABLE IMAGES

Defective images within this document are accurate representations of the original documents submitted by the applicant.

Defects in the images include but are not limited to the items checked:

☒ **BLACK BORDERS**

☐ **IMAGE CUT OFF AT TOP, BOTTOM OR SIDES**

☐ **FADED TEXT OR DRAWING**

☐ **BLURRED OR ILLEGIBLE TEXT OR DRAWING**

☐ **SKEWED/SLANTED IMAGES**

☒ **COLOR OR BLACK AND WHITE PHOTOGRAPHS**

☐ **GRAY SCALE DOCUMENTS**

☐ **LINES OR MARKS ON ORIGINAL DOCUMENT**

☐ **REFERENCE(S) OR EXHIBIT(S) SUBMITTED ARE POOR QUALITY**

☐ **OTHER:** _____

IMAGES ARE BEST AVAILABLE COPY.

As rescanning these documents will not correct the image problems checked, please do not report these problems to the IFW Image Problem Mailbox.